

iQ ONE


TECHNICAL DATA

CERTIFICATION & CLASSIFICATION	STANDARDS	iQ One
Type of floor covering	EN 14565	Homogeneous floor covering based upon synthetic thermoplastic polymers
CE certification	EN 14041	Yes
ISO certification		Ronneby ISO 9001/Ronneby ISO 14001
TECHNICAL CHARACTERISTICS	STANDARDS	iQ One
iQ surface treatment		Yes
Total thickness	ISO 24346 – EN 428	2.0 mm
Wear layer thickness	ISO 24340 – EN 429	2.0 mm
Total weight	ISO 23997 – EN 430	2800 g/m ²
Form of delivery	ISO 24341 – EN 426 (rolls)	Approx. 23 running metres x 200 cm Art. no. 21200_ _ _ 3 digit colour colour number
TECHNICAL PERFORMANCES	STANDARDS	iQ One
Dimensional stability	EN 14565 Annex C AS/ISO 9239.1	≤ 0.20 % Critical radiant flux 10.5kW/m ²
Reaction to fire	AS/NZ 3837 (wall)	Smoke 33%.min Group 3
Residual indentation	ISO 24343-1 – EN 433	Required value: ≤ 0.10 mm Best measured value: 0.02 mm
Castor chair test	ISO 4918 – EN 425	Suitable
Static electrical discharge	EN 1815	< 2 kV
Total VOC emissions	ISO 16000-6	≤ 100 µg/m ³ (after 28 days)
Underfloor heating		Suitable – max 27°C
Light fastness	EN ISO 105-B02	≥ level 6
Chemical resistance	ISO 26987 – EN 423	Excellent
Slip resistance	DIN 51130 AS 4586	R9 P4
Wet room approval	EN 13553 Annex A GBR approval system	Watertight Certified
Flexibility	ISO 24344 – EN 435	Pass
Colours		38

The above information is subject to modification for the benefit of further improvement. (01/17).

CUSTOMS TARIFF : 482050000000F

Tarkett's instructions regarding installation, cleaning and maintenance should be observed.
Please contact Tarkett at the address shown for these instructions.



According to European Classification ISO 10874 - EN 685



iQ
NEW FOR LIFE™



Laying
direction