



Linoleum xf



Technical data	Standards	Veneto xf			Veneto Acoustic xf	Veneto Tiles xf	Silencio xf	Veneto Soluzione xf	Allegro xf	Etrusco xf
		2.0 mm	2.5 mm	3.2 mm						
Total thickness	EN 428	2.0 mm	2.5 mm	3.2 mm	4.0 mm	2.5 mm	3.8 mm	10 mm	2.5 mm	2.5 mm
Classification	EN 685	Classes:	Classes:	Classes:	Classes:	Classes:	Classes:	Classes:	Classes:	Classes:
	Domestic	23	23	23	23	23	23	23	23	23
	Commercial	32	34	34	33	34	33	32	34	34
	Light industrial	41	42	42	41	42	41	42	42	42
	UPEC	U2S2E1C2	U4P3E1/2C2	U4P3E1/2C2			U4P3E1/2C2		U4P3E1/2C2	U4P3E1/2C2
Total weight	EN 430	ca. 2 400 g/m ²	ca. 3 000 g/m ²	ca. 3 900 g/m ²	ca. 4 500 g/m ²	ca. 3 150 g/m ²	ca. 3 350 g/m ²	ca. 8 600 g/m ²	ca. 3 000 g/m ²	ca. 3 000 g/m ²
Residual indentation	EN 433	ca. 0.07 mm	ca. 0.08 mm	ca. 0.10 mm	ca. 0.25 mm	ca. 0.08 mm	≤ 0.20	max. 0.12 mm	ca. 0.08 mm	ca. 0.08 mm
Castor chair	EN 425	Suitable for office chairs with castors type W (Norm EN 12529).								
Dimensional stability	EN 669					Variation ≤ 0.10 %				
Type of floorcovering	EN 686						Linoleum on a foam backing			
	EN 687				Linoleum on a corkment backing					
	EN 14085							Floor panels for loose laying		
Flexibility	EN 435 Method A	≤ 25 mm Ø	≤ 30 mm Ø	≤ 40 mm Ø	≤ 30 mm Ø	≤ 30 mm Ø	≤ 30 mm Ø		≤ 30 mm Ø	≤ 30 mm Ø
Fire classification	EN 13501-1	C _n s1	C _n s1	C _n s1	C _n s1	C _n s1	C _n s1	C _n s1	C _n s1	C _n s1
Cigarette burns	EN 1399	Resistant to cigarette burns.								
Static electrical propensity	EN 1815	< 2 kV	< 2 kV	< 2 kV	< 2 kV	< 2 kV	< 2 kV	< 2 kV	< 2 kV	< 2 kV
Impact sound reduction	ISO 140-8 EN ISO 717-2	5 dB	6 dB	9 dB	14 dB	6 dB	17 dB	16 dB	6 dB	6 dB
Impact sound reduction with Elafono*	ISO 140-8 EN ISO 717-2	14 dB	15 dB	15 dB					15 dB	15 dB
Light fastness	ISO 105-B02 Method 3	≥ 6	≥ 6	≥ 6	≥ 6	≥ 6	≥ 6	≥ 6	≥ 6	≥ 6
Chemical resistance	EN 423	Resistant to dilute acids, oils, fats and current solvents and alkalis.								
Thermal resistance	EN 12524	0.012 m ² K/W	0.015 m ² K/W	0.019 m ² K/W	0.040 m ² K/W	0.015 m ² K/W	0.040 m ² K/W	0.098 m ² K/W	0.015 m ² K/W	0.015 m ² K/W
Underfloor Heating		Suitable	Suitable	Suitable	Suitable	Suitable	Suitable	Suitable	Suitable	Suitable
Colours		50	50	6	on request	on request	12	12 on request	8	10
Form of delivery (rolls)	EN 426	20-30 lm x 2 m			ca. 20 lm x 2 m		ca. 20 lm x 2 m		20-30 lm x 2 m	
Form of delivery (tiles)	EN 427									
– Side length						50 x 50 cm		30.5 x 91.5 cm		
– Squareness and straightness						deviation: ≤ 0.50 mm deviation: ≤ 0.35 mm		or 30.5 x 30.5 cm	accordingly	

DESCRIPTION EN 548

Linoleum homogeneous floor-covering on jute backing for rolls and synthetic backing for tiles.

Composition:

Wood and cork flour, linseed oil, natural resins, pigments.

The above information is subject to modifications for the benefit of further improvement (10/08).

To obtain the exact colour of the samples, it is recommended to expose them to sunlight for several hours in order to remove the normal yellowing effect due to the oxidation process.

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

* Elafono:

Description: one-layer under layer made of cork grain and a binding agent on jute backing.

Properties:
sound-reducing effect.

Available:
rolls of 20 to 30 lm x 2 m.

Thickness:
2.0 mm
Ref: 1861030

Also available:

Narnidur xf

- Linear marbled design
- 4 mm thickness designed to withstand heavy traffic
- Ideal for industrial applications
- 8 colours available on request
- Corresponding to 3.2 mm Veneto xf