

Tarkett bv
Mevr. Petra Batenburg
Taxandriaweg 15
5142 PA WAALWIJK
Nederland



Your notice of
12-06-2018

Your reference

Date
30-07-2018

Analysis Report 18.03385.01

Required tests :

EN 13501-1 (2007) + A1 (2009)

Identification number	Information given by the client	Date of receipt
T1814190	Carved EcoBase™	12-06-2018


Kristina De Temmerman

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB




Reference: T1814190 - Carved EcoBase™

Information given by the client

Product standard	EN 13501-1 (2007) + A1 (2009)
Production batch/piece number	WA81010094 / 341362
Date of carpet finishing	28-05-2018
FR treated	yes
FR-surface treatment	no
Type of manufacture	Tufted
Use-surface	PA 6
Substrate, support	Fibre fleece PES
Backing layer	EcoBase™
Total mass	4150 g/m ²
Pile thickness	3.9 mm
Total thickness	7.5 mm
Surface structure	Loop pile

Notified body No: 0493



Reference: T1814190 - Carved EcoBase™

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Product standard EN 13501-1 (2007) + A1 (2009)

Classification of textile floor coverings in accordance with EN 14041 (2004) § 4.1.4

“The textile floor coverings listed in Table 2, in the end uses identified in the table, are classified without further testing (CWFT) in the classes shown and do not require testing in respect of these end uses and classes”.

Table 2 – Classes of reaction to fire for textile floor coverings, classified without further testing

Floor covering type¹	EN product standard	Class³ Floorings
Non-FR machine-made wall-to-wall carpets and pile carpet tiles ²	EN 1307	E _{fl}
Non-FR needled textile floor coverings without pile ²	EN 1470	E _{fl}
Non-FR needled textile floor coverings with pile ²	EN 13297	E _{fl}
¹⁾ Floor covering glued or loose laid over a Class A2-s1,d0 substrate ²⁾ Textile floor coverings having a total mass of max. 4.8 kg/m ² , a minimum pile thickness of 1,8 mm (ISO 1766) and <ul style="list-style-type: none"> - a surface of 100% wool - a surface of 80% wool or more – 20% polyamide or less - a surface of 80% wool or more – 20% polyamide/polyester or less - a surface of 100% polyamide - a surface of 100% polypropylene and if with SBR-foam backing, a total mass of > 0.780 kg/m². All polypropylene carpets with other foam backings are excluded. ³⁾ Class as provided for in Table 2 in the Annex to Decision 2000/147/EC.		

Classification

Class E_{fl}



Reference: T1814190 - Carved EcoBase™

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	24-07-2018
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2007) + A1 (2009)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Fibre cement board - density (1800 ± 200) kg/m ³
Mounting	Loose-laid
Cleaning	Specimens have not been cleaned
Joint	At 25 cm and 75 cm

Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux * kW/m ²
	10 min	20 min	30 min		
Width					
#1	15	18	19	14 min 40 s	9.3
Length					
#1	14	24	31	30 min 00 s	7.0
#2	16	26	31	26 min 30 s	7.0
#3	16	24	30	30 min 00 s	7.2
Average					7.1

* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2007) + A1 (2009)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{fl}	E _{fl}	heat flux ≥ 8,0 kW/m ²
C _{fl}	E _{fl}	heat flux ≥ 4,5 kW/m ²
D _{fl}	E _{fl}	heat flux ≥ 3,0 kW/m ²

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Width		
#1	11	55
Length		
#1	7	41
#2	7	28
#3	11	51
Average		40

Additional classification in accordance with EN 13501-1 (2007) + A1 (2009)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2



Reaction to fire classification : C_n/ s1

*Loose-laid on a non-combustible substrate**

** End use substrates of classes A1 or A2-s1, d0 (EN 13238:2010 § 5.2.2)*

Limitations

This classification document does not represent type approval or certification of the product.